

GridLock Bio/CR-6 Panel

Walls and Ceilings

General Description:

GridLock Bio/CR-6 Wall Surface is part of the LSP GridLock Construction System. Bio/CR-6 panels are 3 mm thick and are made of a composite of materials including polymer filled woven components that form an economical and versatile composite wall or ceiling covering. The exposed face is composed of heavy duty resin/gel coat finish that creates a consistent extra smooth face. The panel finish is semi-gloss and the panel assembly is ASTM E 84 Class A for smoke and flame spread.

The panel will be supplied in standard 4' x 8', 4' x 9' and 4' x 10' sizes. The edges of the mounted panels are held 3/16" apart and the resulting void is filled with a 100% solids Urethane sealant that contains no HAP, no-VOC and create a virtually seamless joint that closely matches the panel surface. The primary features of the GridLock Construction Panels are a non-porous high density surface, high chemical resistance, and a virtual seamless installation. As such the GridLock System does not support the growth of infectious microbes and can be cleaned and disinfected with the rigorous operating protocols required in infectious disease programs.

The Bio/CR-6 "system" is designed to be installed over an existing substrate such as gypsum board or other sound substrates and makes installation economical and fast. Additionally it is a non-porous sealed seamless biocontainment room finish that is ideal for significantly reducing bio-load contaminants. Additionally, the ability to mount these non-porous finished panels to a variety of substrates can reduce construction time and eliminate future maintenance costs.

Bio/CR-6 Panel Typical Applications:

- Procedure Rooms
- Infectious Disease Isolation Areas
- Quarantine Rooms
- Animal Holding
- Cage Wash
- Feed and Bedding Storage

Cleaning: GridLock Wall Panels can withstand daily surface washing, wet wiping, dusting and vacuuming. They are compatible with a wide range of chemical disinfection and fumigation products. Ask your LSP Representative for more detailed maintenance instructions.

The panels have the following properties:

Fire Rating: panel assembly Class 1 ASTM E 84 for flame spread of 25 or less
Light Reflectance @ 85: 94.3
Minimum Weight: 0.8 lbs. per square foot
Finish: Polyester gel coat smooth **Panel thickness:** 3 mm
Color: White
Finish: Semi-Gloss
Hardness: ASTM D-785 46 Barcol
Flexural Mod ASTM D-790-07: 557,693
Flexural Strength-ASTM D 790-07: 5325 psi
Water Vapor Transmission ASTM E-96: < 0.0001 perms
Air Permeance ASTM E-2178 (L/s/m²): 0.00001 @ 300 pa

Tensile Strength: ASTM D-638: 3272 psi
Tensile Mod ASTM D-638: 511,000
Coefficient of Linear Thermal Expansion CLTE (mm mm C) ASTM D-696: 4.30 E -05
Compressive Strength ASTM D- 695: 5364 psi
Modulus: ASTM D695: 49,873 psi

Chemical Resistance	20% Acetic Acid	Occasional Spill
	50% Citric Acid	Good
	20% Nitric Acid	Occasional Spill
	30% Hydrochloric Acid	Occasional Spill
	10% Hydrofluoric Acid	Occasional Spill
	Hydrogen Peroxide	Good
	40% Potassium Hydroxide	Good
	40% Sodium Hydroxide	Good
	50% Sulfuric Acid	Good
	Urea	Good
	Commercial Clorox	Good

The joint adhesive/sealant has the following properties:

Hardness Shore D	ASTM D-1706	70 - 80
Tensile Strength	ASTM D-638	3,000 psi min.
Flexural Strength	ASTM D-790	4,000 psi min.
Thermal Shock	Mil F-52505	No cracking or loss of adhesion
Abrasion Resistance (Taber Abrader, CS-17 Wheels, 1000 gm. load, 1000 cycles)	ASTM D-4060	.035 gm loss
Ultimate Elongation	ASTM D-638	20% min.