

SeamTek[®] Ure-Glaze NR Wall & Ceiling Coating

1. Product Description

Basic use

SeamTek[®] Ure-Glaze is a two component 100% solids, low-odor, no VOC, LEED compliant urethane resin that chemically cures to form a highly abrasion resistant binder for high performance interior wall and ceiling finishes. It has been specifically designed to exhibit excellent flow characteristics, air release, and workable viscosity. It is recommended for use as a wall finish in Animal Holding facilities, pharmaceutical production and areas that are subject to water and chemical exposure. Recommended thickness is 12-15 mils over an epoxy primer..

Features and benefits include:

- No amine blush – no frosting
- Color Stable
- Low foaming
- Excellent adhesion properties
- UV Resistant
- 100% solids – solvent free
- No VOC
- Low odor
- Low flammability
- High Taber Resistance

The SeamTek[®] systems are composed of resins and aggregates which utilize the best available technology for safety and performance. All products and systems are extensively field tested prior to use on SeamTek[®] projects.

Composition and Materials

SeamTek[®] Pigmented Urethane is a chemical curing, two component, No-VOC 100 % solids Urethane coating.

Sizes

The binder resin and hardener are packaged in 5 U.S. gallon pails.

Limitations

SeamTek[®] Ure-Glaze must not be used to bridge moving cracks or joints. Non-moving cracks or joints that must be over coated require rigid repairs. See LSP Technical Manual System Specifications for details. Surface or air temperature must be between 65°F minimum and 80°F

maximum and relative humidity below 70%. Lower temperatures will extend cure time and higher temperatures will reduce pot and work life.

Storage and Handling

Because SeamTek[®] Ure-Glaze has a flash point above 200°F (93°C), transportation, storage and handling are less restricted.

Product Health and Safety Information

Refer to container labels and Material Safety Data Sheets available from LSP for health, safety and environmental information. If necessary, call LSP at (800) 638-9874

Applicable Standards

SeamTek[®] Ure-Glaze has been tested in accordance with American Society for Testing and Materials (ASTM) methods. Refer to Table 1 on page 1 for more information. SeamTek[®] Urethane can be used as a wall coating in food processing areas and other similar applications. The USDA and FDA no longer regulates coatings used on floors, walls, and ceilings in food process areas, since the surfaces are not intended for food contact.

Surface Preparatory Work

Preparatory work must be done in accordance with

Table 1 Typical Physical Properties

Property	Measuring Standards and Conditions	Results Part A/Part B
Specific Gravity	ASTM D 70, Fisher #3-247 pycnometer	1.25
Weight +/- 0.4 lbs./gal.	ASTM E 201	10.7 lbs./gal.
Non-volatile Content	ASTM D 1353, 18 hrs. at 200°F (93°C)	100%
Viscosity, cps	LV #3 Spindle, Thix 3.01, 77 degree F	8,850 cps
Flash Point, TCC minimum	Seta Flash	Greater than 200°F (93°C)
Solvent Odor	ASTM D 1296	Extremely low
Pot Life		20 minutes at 72°F (22°C) & 50% R.H.

procedures described in LSP Technical Manual.

Mixing

Caution, containers used to measure SeamTek® Ure-Glaze resin and Harder must be marked appropriately and only used to measure the indicated component. Container used to mix both resin and hardener must be cleaned or changed after mixing each batch to avoid residual material affecting viscosity and cure rates.

Measure both parts by volume 2 parts 231 resin to 1 part 305 hardener into plastic marked containers. Pour resin and hardener into a separate container and agitate using a jiffy paddle and low speed drill (400-600 rpm). Agitate for 2 minutes, then scrape sides of container and mix for an additional minute. Avoid generating air bubbles and foam. Consider mixing small batches to reduce potential waste. To avoid exothermic reaction in mixing container, do not let

mixed components sit in container. Immediately, begin to apply the mixture to the wall surface and do not mix more material than you can apply in 20 minutes. Spread or finish material according to application instructions contained in LSP Technical Manual.

3. Warranty

LSP Performance Resin Wall Systems are installed by LSP Associate Contractors and are available with the LSP Single

Product Data Sheet is for your information and is not a contract nor a product warranty. Your installation contract is provided by your LSP Associate Contractor. LSP's warranty to you is made solely in the LSP Single Source Limited Warranty for Labor and Material. Contact your Associate Contractor for the specific warranty document.

4. Maintenance

SeamTek® Systems are hard seamless surfaces that will provide years of life with little maintenance. For more detailed maintenance instructions, please request LSP Maintenance Instructions. Periodic inspections by your LSP Associate Contractor are recommended to discuss ways to extend the life of the floor care.

5. Technical Service

Call your LSP representative for assistance.

Table 2 – Typical Performance Properties

Property	Measuring Standards and Conditions	Binder Resin Results Only See Note 1 below
Drying time	ASTM D 1475 77°F (25°C)	To Touch: 4 to 6 hrs., max. To complete: 24 hrs. max.
Hardness (indentation)	ASTM D 2240 Rex D Model 1700	65-70 resin only 80-85 with aggregate
Elongation	ASTM D 638	Less than 15 %
Tensile Strength	ASTM D 638	4500 psi (31 MPa)
Water Absorption	ASTM D 570-95	Less than 0.2%
Indentation Resistance	Mil. Std. D-3134	Zero
Water Vapor Transmission	ASTM E 96-94	Less than 0.10 U.S. perms
Weathering Resistance	ASTM G 26 Type B, BH, 300 hrs	UV Stable
Abrasion Resistance	ASTM C 501, CS-17 Wheel, 1000 rev. with 1000 gram weight	Less than 0.1 grams weight loss
Bond Strength to Concrete	ASTM D 4541	350 psi (2.4 to 3.4 MPa) Concrete fails
Electrical Conductivity		Non conductive
Flammability	ASTM D 635	Self-Extinguishing

1. For additional performance properties for binder resin with aggregate added (ie. Tensile Strength, Flexural Strength, Flexural Modulus, Compressive Strength, Coefficient of Linear Expansion, etc.) refer to LSP technical manual for specific system(s) selected.

Source Limited Warranty for Labor and Material. This

LSP Performance Resins
Phone (800) 638-9874
Page 2 of 2

124 Speer Road
UreGlaze NR
Revision # 08.15

Chestertown, MD 21620
www.lspinc.com
Printed 9/8/15